



# WHITE WET STRENGTH KRAFT PAPER



PM5



100% virgin  
fiber



**MANUFACTURED:** Ilim Group, Koryazhma Branch

PROPERTY	VALUE	
Substance, g/m <sup>2</sup> (ISO 536), Min/max	50 ± 4	60 ± 4
Cobb test 60, g/m <sup>2</sup> , max (GOST 12605)	25	
Whiteness without OBA, %, min (GOST 30113),	82	
Tensile Strength CD, N, min (ISO 1924-2)	25	35
Burst, kPA, min (GOST 13525.8)	200	220
Wet Strength, %, min (GOST ISO 1924-2)	22	
Moisture, % (ISO 287)	5,0 - 6,5	
Smoothness, sec, min (GOST 12795)	16	

Test climate (ISO 187). Temperature (23 ± 1) °C, relative humidity (50 ± 2) %